

AMENDMENTS TO THE CLAIMS

1. (Currently amended) A surface-treating process, wherein an inner surface of a vacuum member is mechanically polished in the presence of a liquid medium, or a liquid medium and ~~optionally~~ an oxidizing material,

wherein the liquid medium includes no hydrogen atom, ~~except a hydrogen may be present in the oxidizing material,~~ and

wherein the liquid medium including no hydrogen atom is a liquid at an ordinary temperature and an ordinary pressure and a saturated hydrocarbon in a molecule of which a hydrogen atom or hydrogen atoms are all substituted with a fluorine atom or fluorine atoms.

2. (Cancelled)

3. (Original) A surface-treating process according to claim 1, wherein the vacuum member is made of one kind or two or more kinds selected from the group consisting of niobium, titanium, stainless steel, copper, aluminum and iron.

4. (Original) A surface-treating process according to claim 1, wherein the vacuum member is made of niobium.

5. (Original) A surface-treating process according to claim 1, wherein the vacuum member is a superconducting accelerating cavity.

6. (Original) A surface-treating process according to claim 1, wherein the mechanical polishing is performed in the presence of an oxidizing material.

7. (Original) A surface-treating process according to claim 6, wherein the oxidizing material is ozone, a mixture of ozone and oxygen, or hydrogen peroxide water.

8. (Original) A surface-treating process according to claim 1, wherein after the mechanical polishing, the inner surface of a vacuum member is subjected to chemical polishing or electrochemical polishing.
9. (Original) A surface-treating process according to claim 1, wherein after the mechanical polishing, the inner surface of a vacuum member is subjected to electrochemical polishing using an electrolytic solution including an oxidizing material.
10. (Original) A surface-treating process according to claim 9, wherein the oxidizing material is ozone, hydrogen peroxide water or nitric acid.
11. (Currently amended) A forming process for a vacuum member, wherein the vacuum member is mechanically formed in the presence of a liquid medium, or a liquid medium and ~~optionally~~ an oxidizing material,
wherein the liquid medium includes no hydrogen atom, ~~except a hydrogen may be present in the oxidizing material,~~ and
wherein the liquid medium including no hydrogen atom is a liquid at an ordinary temperature and an ordinary pressure and a saturated hydrocarbon in a molecule of which a hydrogen atom or hydrogen atoms are all substituted with a fluorine atom or fluorine atoms.
- 12-13. (Cancelled)
14. (Withdrawn) An electrolytic polishing solution including an oxidizing material and used in electrochemical polishing of a vacuum member.
- 15-16. (Cancelled)